


PRODUKTDATENBLATT

Raw magnets of Samarium-Cobalt (SmCo)

Block magnet made of SmCo





| Article number | Quality | Lmm | Bmm | Hmm | Adhesive force* N | Weight g | Temperature °C | Magnetisation |
|-----------------|---------|---------------------------------------|--|---------------------------------------|----------------------|----------|----------------|---------------|
| MSAQm7.5x4x1.5 | RCS26H | 7,5 ^{+0.1} / _{-0.1} | 4 ^{+0.1} / _{-0.1} | 1,5 ^{+0.1} / _{-0.1} | 3.4 | 0.4 | 350 | axial |
| MSAQm7.5x6x2 | RCS26H | 7,5 ^{+0.1} / _{-0.1} | 6 ^{+0.1} / _{-0.1} | 2 ^{+0.1} / _{-0.1} | 5 | 0.7 | 350 | axial |
| MSAQm10x7.5x2 | RCS26H | 10 ^{+0.1} / _{-0.1} | 7,5 ^{+0.1} / _{-0.1} | 2 ^{+0.1} / _{-0.1} | 7.5 | 1.2 | 350 | axial |
| MSAQm12x9.5x2.5 | RCS26H | 12 ^{+0.1} / _{-0.1} | 9,5 ^{+0.1} / _{-0.1} | 2,5 ^{+0.1} / _{-0.1} | 11 | 2.5 | 350 | axial |
| MSAQm16x12x2.5 | RCS26H | 16 ^{+0.1} / _{-0.1} | 12,5 ^{+0.1} / _{-0.1} | 2,5 ^{+0.1} / _{-0.1} | 15 | 4 | 350 | axial |
| MSAQm18x16.5x4 | RCS26H | 18 ^{+0.1} / _{-0.1} | 16,5 ^{+0.1} / _{-0.1} | 4 ^{+0.1} / _{-0.1} | 29 | 10 | 350 | axial |
| MSAQm26x20.3x5 | RCS26H | 26 ^{+0.1} / _{-0.1} | 20,3 ^{+0.1} / _{-0.1} | 5 ^{+0.1} / _{-0.1} | 51 | 22 | 350 | axial |
| MSAQm33x26x6.5 | RCS26H | 33 ^{+0.1} / _{-0.1} | 26,3 ^{+0.1} / _{-0.1} | 6,5 ^{+0.1} / _{-0.1} | 85 | 47 | 350 | axial |

PRODUCT NOTE:

SmCo magnets can be produced in almost any desired dimensions and without tooling costs. Small quantities are therefore also possible. The surface is bright. The temperature specification refers to the maximum operating temperature of the material. However, the resistance may be reduced due to the geometry.

As an alternative to the standard, we also offer customised solutions:

- " customer-specific dimensions
- " modified magnetisation direction
- " other types of magnetisation
- " other qualities
- " additional coating (e.g. galvanised, nickel-plated, epoxy-coated)

Magnetised by the height (H)

* The forces have been determined at room temperature on a polished plate made of steel (S235JR according to DIN 10 025) with a thickness of 10 mm (1kg~10N). A deviation of up to -10% from the specified value is possible in exceptional cases. In general, the value is exceeded. The type of application

Gewerbestraße 23

78739 Hardt

T. +49 7422 9519-0



PRODUKTDATENBLATT

(installation situation, temperatures, counter anchors, etc.) sometimes influence the forces enormously. The values given are for orientation purposes. Let our experts advise you.